

Silver Brazing Alloy J4010N

Composition (wt %)									ISO 17672	AWS
Ag	Cu	Zn	Mn	Ni	Sn	Si	P	Other		
40	30	28	-	2	-	-	-	-	Ag 440	BAG-4

Technical data

Density	9 g/cm ³
Melting range	660-780 °C
Shear strength	-
Tensile strength	-
Recommended joint gap	0,1-0,25 mm
Maximum operating temperature of brazed joint	-

Applications

This silver brazing alloy is especially suitable for brazing tools, cemented carbides and materials with low wettability (such as tungsten, tantalum, molybdenum, chromium, etc.), providing a joint with very good mechanical properties. However, joint strength depends on various factors: type of base metals to be joined, type of joint, joint gap, etc. J4010N may reduce corrosion at the interface when employed to join stainless steels. Heat sources commonly employed are flame, induction heating system or furnaces.

Standard forms and dimensions

Product	Feasibility
Wire	✓
Strip	✓
Rods	✓
Flux coated rods	-
Rings	✓

Recommended fluxes

Special FPA, Universal FPA, General FPO.

Note

Silver brazing alloys and dimensions other than those listed in our catalogue are available upon request.

Details included in this technical data sheets are based on our knowledge and experience and are believed to be accurate. All data in this data sheet are merely recommendations and shall not be regarded as an assurance of any properties of the product. *We do not assume any responsibility* and make *no warranty* with respect to the *results* that may be *obtained* and the damages that may occur from the use of the information provided.

Since end use of the product is not under our direct control, it is the user's responsibility to comply with applicable safety and hygiene laws and regulations.